

## MEGAPOXY HT

### NON - SAG HYDROPHILIC EPOXY

Megapoxy HT is suitable for application on overhead, vertical or inclined surfaces. Because of its hydrophilic nature it can be used under damp conditions.

Megapoxy HT is designed for application by spraying equipment and can be applied in thick films on vertical and overhead surfaces. Megapoxy HT is also suitable for applications by brushing, knifing, trowelling and other techniques of placement of epoxy resins, with the exception of casting. The non-sag characteristic assists greatly in underwater applications.

Mixing proportions	: 3 parts "A" to 1 part "B" by volume
Colour when mixed	: Grey
Work time ( 1 litre mix )	: 30 minutes at 25°C
Minimum cure time	: 24 hours at 25°C

### MEGAPOXY HT - TYPICAL CURED PROPERTIES

Maximum operating temperature	: 100°C
Tensile Strength	: 40 MPa
Tensile Shear Strength, steel/steel	: 13 MPa
Compressive Strength	: 100 MPa
Modulus of Elasticity	: 1.1 x 10,000 MPa
Flexural Strength	: 40 MPa
Bond Strength Steel to Concrete	: 2.6 Mpa Concrete Fails

### AVAILABILITY

Megapoxy HT is available in 225ml, 1 litre, 4 litre and 20 litre kits. In each kit Part "A" and Part "B" are premetered in correct mixing ratio for immediate use.

Megapoxy HT



**VIVACITY ENGINEERING PTY. LTD.**

3 Sefton Road, Thornleigh, NSW 2120 • P.O. Box 71, Hornsby, NSW Australia, 1630  
Telephone +61-2-9875 3044 Fax +61-2-9875 3665 email:info@megapoxy.com  
www.megapoxy.com A.B.N. 78 305 545 664